

PINK® BATTs: CEILING

THERMAL INSULATION FOR RESIDENTIAL CEILING APPLICATIONS

Description

Pink® Batts are made from lightweight, flexible and resilient glasswool for thermal and acoustic insulation of residential ceilings. Pink® Batts are available in various sizes to fit standard timber and steel joist spacings.

Application

Pink® Batts are the trusted choice when it comes to constructing new homes or retrofitting existing buildings for increased thermal efficiency. The Pink® Batts insulation range is available in various thermal R-values and dimensions ensuring there is an effective and efficient product solution for every application.

Pink® Batts, renowned for their firmness, are low itch, easy to cut and friction fit standard joists to make homes feel cooler in summer, warmer in winter and provide energy savings all year round.

Physical Characteristics

Material R-value m ² K/W	Nominal Thickness mm	Width mm	Length mm	Batts per pack	m ² per pack	Coverage per pack m ²	Packs per Bale	Product Code
R2.5	130	430	1160	16	8.0	9.0	6	901254
		580	1160	16	10.8	12.2	6	901255
R3.0	155	430	1160	16	8.0	9.0	5	901304
		580	1160	16	10.8	12.2	5	901305
R3.5	175	430	1160	16	8.0	9.0	4	901354
		580	1160	10	6.7	7.6	6	901355
R4.0	195	430	1160	10	5.0	5.6	5	901404
		580	1160	10	6.7	7.6	6	901403
R4.1	195	430	1160	10	5.0	5.6	5	901414
		580	1160	10	6.7	7.6	6	901415
R5.0	215	430	1160	8	4.0	4.5	5	901504
		580	1160	8	5.4	6.1	5	901505
R6.0	250	430	1160	6	3.0	3.4	5	901604
		580	1160	6	4.0	4.6	5	901605
R7.0	285	430	1160	4	2.0	2.3	5	901704
		580	1160	4	2.7	3.0	5	901705

Physical Properties

Property	Test Method/Standard	Result	Unit
Maximum Service Temperature	ASTM C411/C447	350	°C
Thermal Resistance	AS/NZS 4859.1:2002	Complies	m ² .K/W
Moisture Absorption	When exposed to environmental conditions of 50°C and 95% relative humidity for four days	<0.2%	% by volume
pH	ASTM C871	9 (does not contribute to the corrosion of steel structures)	—

For more information call 1300 654 444
email info@insulation.com.au or web www.insulation.com.au



Fire Hazard Properties

Property	Test Method/Standard	Result
Combustibility	AS/NZS 1530.3:1999	Non combustible
Ignitability Index		0
Spread of Flame Index		0
Heat Evolved Index		0
Smoke Developed Index		0-1
BAL Compliance	AS3959:2018	Low – FZ

Acoustic Performance

Sound Absorption

Pink® Batts tested achieve the following sound absorption coefficients when tested in accordance with AS ISO 354-2006.

**Sound Absorption Coefficients
at Frequencies (Hz) of:**

Product	Thickness mm	125	250	500	1000	2000	4000	NRC	αw
Pink® Batts R3.5	175	0.55	1.0	1.0	1.0	1.0	1.0	1.10	1.0

Flow Resistivity

Pink® Batts tested achieve the following Flow Resistivities when tested in accordance with ASTM C522-03.

Thickness mm	130	155	175	195	215	250
R-Value	2.5	3.0	3.5	4.0	5.0	6.0

Property	Test Method/Standard	Test Results						Unit
Airflow resistance of acoustic materials	ASTM C522-03	2470	2850	2700	3160	4500	4460	Rayls/m

Health and Safety

Fletcher Insulation glasswool products are manufactured from FBS-1 Glasswool Bio-Soluble Insulation®. FBS-1 Glasswool Bio-Soluble Insulation® is safe to use and classified as non-hazardous according to the criteria of Safe Work Australia. Fletcher Insulation glasswool insulation can be used with confidence in any residential, commercial or industrial application.

Environmental Properties

Fletcher Insulation avoids the use of Ozone Depleting Potential (ODP) substances in the manufacture or composition of its FBS-1 Glasswool Bio-Soluble Insulation® and Sisalation® reflective foil products.

The use of these Fletcher Insulation products guarantees the use of Zero ODP insulation while also ensuring that no harmful levels of Volatile Organic Compounds (VOCs) are released. This allows the incorporation of environmentally preferable insulation whilst also maintaining indoor air quality.

Technical Specification

When specifying, state the following:

The insulation material shall be Fletcher Insulation Pink® Batts Ceiling R _____ m²K/W (Material R-value)
_____ (thickness) x _____ (width) x _____ (length) mm.

© Fletcher Insulation Pty Limited 2020. Fletcher Insulation reserves the right to change product specifications without prior notification. Information in this publication and otherwise supplied to users as to the subject product is based on our general experience and is given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of products, no warranty is given or is to be implied with respect to either such information or the product itself, in particular the suitability of the product for any particular purpose. The purchaser should independently determine the suitability of the product for the intended application. The colour PINK, Pink® and Pink™ Batts are registered trademarks of Owens Corning used under licence by Fletcher Insulation. FBS-1 Glasswool Bio-Soluble Insulation® is a registered trademark of ICANZ. Unless otherwise stated all ™ and ® are trademarks and registered trademarks of Fletcher Insulation Pty Limited ABN 72 001 175 355. RTDS9_Revision_1_Issue Date 15122020.

For more information call 1300 654 444
email info@insulation.com.au or web www.insulation.com.au

